



Korea Ocean Energy Co., Ltd.
(주)코리아해양에너지

ISO 8217 2017 MARINE RESIDUAL FUELS

MARINE RESIDUAL FUELS

Limit	Parameter	RMA	RMB	RMD	RME	RMG				RMK		
		10	30	80	180	180	380	500	700	380	500	700
Max.	Viscosity at 50°C (mm ² /s)	10.00	30.00	80.00	180.0	180.0	380.0	500.0	700.0	380.0	500.0	700.0
Max.	Density at 15°C (kg/m ³)	920.0	960.0	975.0	991.0	991.0				1010.0		
Max.	Micro Carbon Residue (% m/m)	2.50	10.00	14.00	15.00	18.00				20.00		
Max.	Aluminium + Silicon (mg/kg)	25	40		50	60						
Max.	Sodium (mg/kg)	50	100		50	100						
Max.	Ash (% m/m)	0.040	0.070			0.100				0.150		
Max.	Vanadium (mg/kg)	50	150			350				450		
Max.	CCAI	850	860			870						
Max.	Water (% V/V)	0.30	0.50									
Max.	Pour point (upper) in Summer (°C)	6			30							
Max.	Pour point (upper) in Winter (°C)	0			30							
Min.	Flash point (°C)	60.0										
Max.	Sulphur (% m/m)	To comply with statutory requirements as defined by purchaser										
Max.	Total Sediment, aged (% m/m)	0.10										
Max.	Acid Number (mgKOH/g)	2.5										
	Used lubricating oils (ULO): Calcium and Zinc; or Calcium and Phosphorus (mg/kg)	The fuel shall be free from ULO, and shall be considered to contain ULO when either one of the following conditions is met: Calcium > 30 and zinc > 15; or Calcium > 30 and phosphorus > 15.										
Max.	Hydrogen sulphide (mg/kg)	2.00										